

INTERNATIONAL STANDARD

ISO
5832-1

Third edition
1997-07-15

Implants for surgery — Metallic materials —

Part 1: Wrought stainless steel

Implants chirurgicaux — Produits à base de métaux —

Partie 1: Acier corroyé inoxydable

This material is reproduced from ISO documents under International Organization for Standardization (ISO) Copyright License number IHS/ICC/1996. Not for resale. No part of these ISO documents may be reproduced in any form, electronic retrieval system or otherwise, except as allowed in the copyright law of the country of use, or with the prior written consent of ISO (Case postale 56, 1211 Geneva 20, Switzerland, Fax +41 22 734 10 79), IHS or the ISO Licensor's members.



Reference number
ISO 5832-1:1997(E)

ISO 5832-1:1997(E)

Contents

Page

| | | |
|-----|--|---|
| 1 | Scope | 1 |
| 2 | Normative references | 1 |
| 3 | Chemical composition | 2 |
| 4 | Microstructure in fully annealed condition | 2 |
| 4.1 | Grain size | 2 |
| 4.2 | Absence of delta ferrite | 2 |
| 4.3 | Inclusion content | 2 |
| 5 | Mechanical properties | 3 |
| 5.1 | Test pieces | 3 |
| 5.2 | Tensile test | 3 |
| 6 | Test methods | 3 |

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 5832-1 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

This third edition cancels and replaces the second edition (ISO 5832-1:1987), which has been technically revised.

ISO 5832 consists of the following parts, under the general title *Implants for surgery — Metallic materials*:

- *Part 1: Wrought stainless steel*
- *Part 2: Unalloyed titanium*
- *Part 3: Wrought titanium 6-aluminium 4-vanadium alloy*
- *Part 4: Cobalt-chromium-molybdenum casting alloy*
- *Part 5: Wrought cobalt-chromium-tungsten-nickel alloy*
- *Part 6: Wrought cobalt-nickel-chromium-molybdenum alloy*
- *Part 7: Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy*
- *Part 8: Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy*
- *Part 9: Wrought high nitrogen stainless steel*
- *Part 10: Wrought titanium 5-aluminium 2,5-iron alloy*
- *Part 11: Wrought titanium 6-aluminium 7-niobium alloy*
- *Part 12: Wrought cobalt-chromium-molybdenum alloy*

Introduction

No known surgical implant material has ever been shown to cause absolutely no adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in this part of ISO 5832 has shown that an acceptable level of biological response can be expected, when the material is used in appropriate applications.

SAKY STEEL CO., LTD.

Implants for surgery — Metallic materials —

Part 1: Wrought stainless steel

1 Scope

This part of ISO 5832 specifies the characteristics of, and corresponding test methods for, wrought stainless steel for use in the manufacture of surgical implants.

Provision is made for two types of stainless steel based on chemical composition (see table 1).

NOTE — The mechanical properties of a sample obtained from a finished product made of this alloy may not necessarily comply with the specifications given in this part of ISO 5832.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 5832. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 5832 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 377-1:1989, *Selection and preparation of samples and test pieces of wrought stainless steels — Part 1: Samples and test pieces for mechanical tests.*

ISO 404:1992, *Steel and steel products — General technical delivery requirements.*

ISO 437:1982, *Steel and cast iron — Determination of total carbon content — Combustion gravimetric method.*

ISO 439:1982, *Steel and cast iron — Determination of total silicon — Gravimetric method.*

ISO 629:1982, *Steel and cast iron — Determination of manganese content — Spectrophotometric method.*

ISO 643:1983, *Steels — Micrographic determination of the ferritic or austenitic grain size.*

ISO 671:1982, *Steel and cast iron — Determination of sulphur content — Combustion titrimetric method.*

ISO 10714:1992, *Steels and cast iron — Determination of phosphorus content — Phosphovanadomolybdate spectrophotometric method.*

ISO 4967:—¹⁾, *Steel — Determination of content of non-metallic inclusions — Micrographic method using standard diagrams.*

ISO 6892:—²⁾, *Metallic materials — Tensile testing at ambient temperatures.*

1) To be published. (Revision of ISO 4967:1979)

2) To be published. (Revision of ISO 6892:1984)

3 Chemical composition

3.1 Test samples

The selection of samples for analysis shall be carried out in accordance with ISO 377-1.

3.2 Cast analysis

The cast analysis of the steel when determined in accordance with clause 7 shall comply with the chemical composition specified in table 1. The molybdenum and chromium contents shall be such that the C value obtained from the formula given below is not less than 26.

$$C = 3,3w_{\text{Mo}} + w_{\text{Cr}}$$

where

w_{Mo} is the molybdenum content, expressed as a percentage by mass;

w_{Cr} is the chromium content, expressed as a percentage by mass.

Table 1 — Chemical composition

| Element | Compositional limits, % (m/m) | |
|------------|-------------------------------|---------------|
| | Composition D | Composition E |
| Carbon | 0,030 max. | 0,030 max. |
| Silicon | 1,0 max. | 1,0 max. |
| Manganese | 2,0 max. | 2,0 max. |
| Phosphorus | 0,025 max. | 0,025 max. |
| Sulfur | 0,010 max. | 0,010 max. |
| Nitrogen | 0,10 max. | 0,10 to 0,20 |
| Chromium | 17,0 to 19,0 | 17,0 to 19,0 |
| Molybdenum | 2,25 to 3,5 | 2,35 to 4,2 |
| Nickel | 13,0 to 15,0 | 14,0 to 16,0 |
| Copper | 0,50 max. | 0,50 max. |
| Iron | Balance | Balance |

4 Microstructure in fully annealed condition

4.1 Grain size

The austenitic grain size, determined in accordance with clause 6, shall not be coarser than grain size No. 4.

4.2 Absence of delta ferrite

The steel shall have a structure free from delta ferrite when examined in accordance with clause 6.

4.3 Inclusion content

The non-metallic inclusion content of the steel, determined at the billet stage, from a billet not exceeding 15 cm thickness, and in accordance with clause 6, shall not exceed the limits given in table 2.

NOTE — It may be necessary to use a special manufacturing technique, such as vacuum or electroslag melting, to produce a steel complying with these cleanliness requirements.

Table 2 — Inclusion content limits

| Type of inclusion | Inclusion content reference number | |
|----------------------|------------------------------------|-------|
| | Thin | Thick |
| A — Sulfides | 1,5 | 1 |
| B — Aluminates | 1,5 | 1 |
| C — Silicates | 1,5 | 1 |
| D — Oxides, globular | 1,5 | 1 |

5 Mechanical properties

5.1 Test pieces

The selection and preparation of samples and test pieces for tensile testing shall be in accordance with ISO 377-1.

5.2 Tensile test

The tensile properties of the steel in the form of bars, wires, and sheet and strip, when tested in accordance with clause 6, shall comply with the values specified in tables 3, 4 and 5, respectively.

Should any of the test pieces not meet the specified requirements or break outside the gauge limits, retests shall be carried out in accordance with ISO 404.

6 Test methods

The test methods to be used in determining compliance with the requirements of this part of ISO 5832 shall be those given in table 6.

Table 3 — Mechanical properties of bars

| Condition | Steel composition | Diameter or thickness <i>d</i> mm | Tensile strength <i>R_m</i> MPa | Proof stress of nonproportional elongation <i>R_p 0,2</i> min. MPa | Percentage elongation after fracture ²⁾ <i>A</i> min. % |
|-------------|-------------------|---|---|---|---|
| Annealed | D | all | $490 \leq R_m \leq 690$ | 190 | 40 |
| | E | | $590 \leq R_m \leq 800$ | 285 | 40 |
| Cold-worked | D and E | < 19 | $860 \leq R_m \leq 1\,100$ ¹⁾ | 690 | 12 |

1) For special implants, higher strength may be required. In such cases the elongation may be correspondingly low.

2) Gauge length = $5,65\sqrt{S_0}$ or 50 mm, where S_0 is the original cross-sectional area, in square millimetres.

Table 4 — Mechanical properties of wires

| Condition | Steel composition | Diameter d mm | Tensile strength R_m MPa | Percentage elongation after fracture ²⁾ A min. % |
|--------------------------|-------------------|--------------------------|----------------------------------|--|
| Annealed | D and E | $0,025 \leq d \leq 0,13$ | $\leq 1\,000$ | 30 |
| | | $0,13 < d \leq 0,23$ | ≤ 930 | 30 |
| | | $0,23 < d \leq 0,38$ | ≤ 890 | 35 |
| | | $0,38 < d \leq 0,5$ | ≤ 860 | 40 |
| | | $0,5 < d \leq 0,65$ | ≤ 820 | 40 |
| | | $> 0,65$ | ≤ 800 | 40 |
| Cold-drawn ¹⁾ | D and E | $0,2 \leq d \leq 0,7$ | $1\,600 \leq R_m \leq 1\,850$ | — |
| | | $0,7 < d \leq 1$ | $1\,500 \leq R_m \leq 1\,750$ | — |
| | | $1 < d \leq 1,5$ | $1\,400 \leq R_m \leq 1\,650$ | — |
| | | $1,5 < d \leq 2$ | $1\,350 \leq R_m \leq 1\,600$ | — |

1) Wire ordered in the cold-drawn condition can be supplied to higher tensile strength levels as specified by the purchaser.

2) Gauge length = $5,65\sqrt{S_0}$ or 50 mm, where S_0 is the original cross-sectional area, in square millimetres.

Table 5 — Mechanical properties of sheet and strip

| Condition | Steel composition | Tensile strength R_m MPa | Proof stress of non-proportional elongation $R_p 0,2$ min. MPa | Percentage elongation after fracture ¹⁾ A min. % |
|---------------|-------------------|----------------------------------|---|--|
| Annealed | D | $490 \leq R_m \leq 690$ | 190 | 40 2) |
| | E | $600 \leq R_m \leq 800$ | 300 | 40 2) |
| Cold-finished | D | ≥ 610 | 300 | 35 |
| | E | ≥ 650 | 390 | 35 |
| Cold-worked | D and E | $860 \leq R_m \leq 1\,100$ | 690 | 12 |

1) Gauge length = $5,65\sqrt{S_0}$ or 50 mm, where S_0 is the original cross-sectional area, in square millimetres.

2) For thickness less than 3 mm: 38 %.

Table 6 — Test methods

| Parameter | Relevant clause or subclause | Test method |
|--|------------------------------|--|
| Chemical composition Carbon Silicon Manganese Sulfur Phosphorus Other elements | 3 | ISO 437 ISO 439 ISO 629 ISO 671 ISO 10714 Recognized analytical procedures (ISO methods where these exist) |
| Grain size | 4.1 | ISO 643 NOTE — It is preferred that samples for grain size determination be selected after the last annealing operation and prior to the final cold-working operation. If samples are selected after a final cold-working operation, transverse specimens should be prepared. |
| Absence of delta ferrite | 4.2 | a) Metallographically prepare specimens in the annealed condition, from longitudinal and transverse sections. b) Using recognized techniques, examine the specimens at $\times 100$ magnification for the presence or absence of delta ferrite. |
| Inclusion content | 4.3 | ISO 4967, Method A, Plate II |
| Mechanical properties Tensile strength Proof stress of nonproportional elongation Percentage elongation | 5 | ISO 6892 |

YAKY STEEL CO., LTD.

ICS 11.040.40

Descriptors: medical equipment, surgical implants, metallurgical products, wrought products, stainless steels, specifications, materials specifications, chemical composition, microstructure, corrosion resistance, mechanical properties, tests.

Price based on 5 pages
